



ROHS Material Declaration

Product Series	Material	ROHS Compliant	Pb Free Termination	Maximum Solder Temperature (°C)	% by Weight																									
					Ba	Zr	Ca	Sr	Nd	Nb	Mg	Ti	Pd	Ag	Ni	Sn	Cu	Al	Rh	Sm	Bi	Pr	Zn	Pb	Cd	Cr VI	Hg	PBDE	PBB	Trace of other Elements
HVC	NPO ≤220 pF	Y▼	Y	265	0	40	25	10	0	0	0.2	1.5	0	0	3	7	10	0.7	2.6	0	0	0	0	0	0	0	0	0	0	0.00
	NPO ≤220 pF (Super term.)	Y▼	Y	265	0	39	24	9	0	0	0.2	1.5	0	3	3	7	10	0.7	2.6	0	0	0	0	0	0	0	0	0	0	0.00
	NPO >220 pF	Y	Y	265	12	1	0	0	34	0	0	26.74	2	10	3	7	0	0.3	2.5	0	0	1.08	0.2	0.4*	0	0	0	0	0	0.18
	NPO >220 pF (Super term.)	Y	Y	265	11	1	0	0	33	0	0	26.74	1	13	3	7	0	0.3	2.5	0	0	1.08	0.2	0.4*	0	0	0	0	0	0.18
	X7R	Y	Y	265	58	0	0	0	0.4	0.7	0	19	1	10	3	7	0	0.2	0	0	0.54	0	0	0	0	0	0	0	0	0.16
	X7R (super term.)	Y	Y	265	57	0	0	0	0.4	0.7	0	18	1	12	3	7	0	0.2	0	0	0.54	0	0	0	0	0	0	0	0	0.16
SCC	NPO ≤220 pF	Y▼	Y	265	0	40	25	10	0	0	0.2	1.5	0	0	3	7	10	0.7	2.6	0	0	0	0	0	0	0	0	0	0.00	
	NPO ≤220 pF (Super term.)	Y▼	Y	265	0	39	24	9	0	0	0.2	1.5	0	3	3	7	10	0.7	2.6	0	0	0	0	0	0	0	0	0	0.00	
	NPO >220 pF	Y	Y	265	12	1	0	0	34	0	0	26.75	2	10	3	7	0	0.3	2.5	0	0	1.07	0.2	0.4*	0	0	0	0	0.18	
	NPO >220 pF (Super term.)	Y	Y	265	11	1	0	0	33	0	0	26.75	1	13	3	7	0	0.3	2.5	0	0	1.07	0.2	0.4*	0	0	0	0	0.18	
	X7R	Y	Y	265	58	0	0	0	0.4	0.7	0	19	1	10	3	7	0	0.2	0	0	0.54	0	0	0	0	0	0	0	0.16	
	X7R (super term.)	Y	Y	265	57	0	0	0	0.4	0.7	0	18	1	12	3	7	0	0.2	0	0	0.54	0	0	0	0	0	0	0	0	0.16
TCX	X7E	Y	Y	265	54	0	0	0	0.3	0.6	0	21	2	10	3	7	0	1.2	0.5	0.3844	0	0	0	0	0	0	0	0	0.02	
LDC	X7E	Y	Y	265	54	0	0	0	0.3	0.6	0	21	2	10	3	7	0	1.2	0.5	0.3844	0	0	0	0	0	0	0	0	0.02	
NCC	NPO	Y	Y	265	44	0	0	0	0	0	15	0	0	4	21	7	0.2	0	0	0	3.5	5.3	0	0	0	0	0	0	0.00	
	X7R	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	
	X5R	Y	Y	265	51	0	0	0	0	0.03	0	12	0	0	15	10	6	0.3	0.3	0	0	0	5.37	0	0	0	0	0	0.00	
	Y5V	Y	Y	265	50.4	0	0	0	0	0	0	13	0	0	5.25	22	2.3	0.1	0	0.35	0	2.1	4.5	0	0	0	0	0	0.00	
HCC	X7R	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	
	X5R	Y	Y	265	51	0	0	0	0	0.03	0	12	0	0	15	10	6	0.3	0.3	0	0	0	5.37	0	0	0	0	0	0.00	
	Y5V	Y	Y	265	50.4	0	0	0	0	0	0	13	0	0	5.25	22	2.3	0.1	0	0.35	0	2.1	4.5	0	0	0	0	0	0.00	
HCN	NPO	Y	Y	265	18.28	0	0	0	21.9	0	0.23	34.06	0.28	10	3	7	0	0.2	0	0.65	0	0.3	1.3	1.7*	0	0	0	2.80		
HCX	X7R	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	
VAC	X5R	Y	Y	265	51	0	0	0	0	0.03	0	12	0	0	15	10	6	0.3	0.3	0	0	0	5.37	0	0	0	0	0	0.00	
	Y5V	Y	Y	265	50.4	0	0	0	0	0	0	13	0	0	5.25	22	2.3	0.1	0	0.35	0	2.1	4.5	0	0	0	0	0	0.00	
HCY	Y5U	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	
RFC	NPO	Y	Y	265	48	0	0	0	0	0	18	0	0	5	18	0	2.2	0	0	0	3.5	5.3	0	0	0	0	0	0.00		
MCA	NPO	Y	Y	265	44	0	0	0	0	0	15	0	0	4	21	7	0.2	0	0	0	3.5	5.3	0	0	0	0	0	0	0.00	
	X7R	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	
	Y5V	Y	Y	265	50.4	0	0	0	0	0	0	13	0	0	5.25	22	2.3	0.1	0	0.35	0	2.1	4.5	0	0	0	0	0	0.00	
SAC	X7R	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	
	Y5U	Y	Y	265	51	0	0	0	0.6	1.2	0	20	0	0	13	12	1	0.3	0.3	0	0	0	0.6	0	0	0	0	0	0.00	

* : Some dielectrics may trace Pb in internal ceramic insert – exempt from RoHS annex 7 to Article 4.1
 ▼ : The ROHS Compliant version (BME) is currently being phased in. The ROHS requirement needs to be added to the PO.
 Due to variation in Capacitance values, voltages and sizes, the numbers are all typical.